

May 2011



TRACKER TECH & HOW-TO

GENERAL INSTRUCTION

GALVA-SHIELD PAINT TOUCH UP

THE FOLLOWING PRESENTATION WILL PROVIDE YOU BASIC INSTRUCTION TO TOUCH UP PAINT ON GALVA-SHIELD APPLICATIONS.

THE INFORMATION PROVIDED IS A RESOURCE FOR INSTRUCTION INTENDED AS A GENERAL GUIDE FOR THIS AND OTHER SIMILAR APPLICATIONS. SPECIFICATIONS ARE ALWAYS SUBJECT TO CHANGE IN THE MANUFACTURING PROCESS SO SOME PORTIONS OF THIS GUIDE MAY NOT DIRECTLY APPLY TO CERTAIN BOATS AND MODELS.

TRACKER MARINE GROUP ASSUMES NO LIABILITY FOR ANY UNFAVORABLE RESULTS AS A RESULT OF USING THIS GENERAL GUIDE FOR REFERENCE OF INSTALLATION.

Galva-Shield Paint Touch Up Procedure

Task Description:

- To repair painted Galva-Shield material and provide optimal rust protection.

Safety First:

- Always wear personal protective equipment when making repairs.
- Only apply primer and paint in a well ventilated area.
- Read and understand paint and primer manufactures warnings before use.

Equipment/Materials required:

- Dual Action (DA) Sander with 150 grit paper
- Isopropanol alcohol or paint thinner.
- Tack cloth
- Primer: Z.R.C. Gavalite Galvanize Compound. Tracker Marine Part # 63772.
- Top color paint.

Use DA Sander with 150 grit sand paper and feather out smooth the area to be painted.



Blow with compressed air.

Clean area with isopropanol alcohol or paint thinner.

Allow to dry.

Mask off area to be painted.



Galva-Shield Paint Touch Up Procedure

Wipe with tack cloth.



Prime with Z.R.C. Gavalite Galvanize Compound.

- Hold can 12 inches from surface.
- Spray in light coats.
- Let dry for 15 minutes.
- Requires 3 mil dry film thickness.

Note: Dry time will vary depending on environment.



Spray with top color using same method as above.

Apply as needed to achieve proper coverage.

Allow 1 hour to dry.

Paint and primer thickness should not exceed 6 mils.

Note: Total cure time 24 hours.

