

# **Service Bulletin**

Bulletin No.: 19-NA-255

Date: January, 2024

# **TECHNICAL**

Subject: Wax Coating on Frame Peeling, Metal Shows Corrosion/Rusting (U.S. and

Canada Only)

Attention: This Bulletin also applies to any of the models that may be Export from North America

vehicles.

Duonali	Model:	Model Year:		VIN:		Engine:	Transmission:
Brand:		from	to	from	to		
Cadillac	Escalade Models	2011	2024				
	Avalanche	2011	2013	]			
	Express		2024	]			
	Suburban	2011					
Chevrolet	Tahoe						
	Silverado	2011	2018	]			
	Silverado 1500 (New Model - 12th VIN Digit = 7) - 4WD		2019				
	Silverado 1500 (New Model)	2019				All	All
	Silverado LD					7	/
	Silverado 2500/3500						
	Silverado 1500	2020	2021				
	Silverado 2500HD/3500HD	2020	2024	]			
	Silverado 1500 LTD (RPO J21, VIN Digit 5 = W / Y)	2022	2022				
	Silverado 1500 New (RPO J22, VIN Digit 5 = A / D)	2022	2022				
	Silverado 1500	2023	2024				

Brand:	Model:	Model Year:		VIN:		Engine:	Transmission:
		from	to	from	to	]	
GMC	Savana	2011	2024	-			
	Yukon Models	2011					
	Sierra	2011	2018				
	Sierra 1500 (New Model)		2019				
	Sierra Limited	2019					
	Sierra 2500/3500					All	All
	Sierra 1500	2020	2021				
	Sierra 2500HD/3500HD	2020	2024				
	Sierra 1500 Limited (RPO J21, VIN Digit 5 = 8 / 9)	2022	2022				
	Sierra 1500 New (RPO J22, VIN Digit 5 = H / U)	2022	2022				
	Sierra 1500	2023	2024				

# Involved Region or Country North America, Europe, Middle East, Israel, Palestine, Chile, Columbia, Ecuador, Paraguay, Peru, Uruguay, Japan, S Korea, China, Taiwan, Thailand, Africa and Egypt, Russia, Uzbekistan, S. Africa, Australia and New Zealand. Some customers may comment that areas of the frame wax coating are peeling off and rust/corrosion is visible on the metal in these areas. Several examples of this condition are shown in each group of graphics below. Truck Example Photos Condition

Bulletin No.: 19-NA-255 January, 2024 Page 3





Page 4 January, 2024 Bulletin No.: 19-NA-255

# Van Example Photos



3396076



3396078



3396079



3396080

### Cause

The cause of this condition may be that the frame supplier may not have properly prepped the metal before the wax coating was applied.

### Correction

Note: A combination of specialized metal coating products manufactured by Lloyds and Daubert have been found to be the most suitable products to provide corrosion control and protection to address this type of repair. Our recommendation is to prep the metal surface using \*Lloyd's Pure Prep™ Metal Surface Preparation P/N 25418, then topcoat with both \*Lloyds Kryptonite™ Metal Treatment\* - P/N 36500 High Temp Satin Black 455 ml (16 oz), and \*Daubert Non-Rust® P/N X-121B One Coat Rust Preventative Coating. It is strongly recommended they be applied according to the manufacturer's procedures.

\*We believe this source and their products to be reliable. There may be additional manufacturers of such products/materials. General Motors does not endorse, indicate any preference for, or assume any responsibility for the products or material from this firm or for any such items that may be available from other sources.

Prep the frame and apply the Lloyds and Daubert coatings following the steps in the Service Procedure below:

### **Service Procedure**

Important: Important: Service agents must comply with all International, Federal, State, Provincial, and/or Local laws applicable to the activities it performs under this bulletin, including but not limited to handling, deploying, preparing, classifying, packaging, marking, labeling, and shipping dangerous goods. In the event of a conflict between the procedures set forth in this bulletin and the laws that apply to your dealership, you must follow those applicable laws.

**Important:** To ensure proper coating performance, all of the manufacturer's "Applications Guidelines" MUST be followed.

**Note:** The graphics below show the bed and/or cab removed from the vehicle. These pictures are provided for reference only. Bed and/or Cab removal are not necessary. Dealers should only repair the locations that show the condition. The following procedure should be utilized to return the truck to a factory look.

 Raise and suitably support the vehicle. Refer to Lifting and Jacking the Vehicle in the Service Manual.




2708909

- If labels are in the area to be reworked, remove any of the visible white labels on the frame (usually one per side).
- 3. Remove any components as required to gain access to the corroded component or area.

**Important:** Any corrosion damage noted to the extent of weakening the component will require component replacement.

4. Determine a start and finish point on each side for the section/area of the frame to be repaired.



3611133

5. Using a rag and wax/grease removing solvent, remove the wax coating and any grease, oil, or undercoating from the truck frame in the affected repair area. The graphic above shows an example of a small portion of the wax coating removed.



2708911

**Important:** Lloyds Kryptonite is designed to apply directly onto brown rust or clean surfaces; however any loose flakes/scale of rust need to be removed prior to application.

- 6. Any loose rust or loose flakes should be scraped, wire brushed or ground off.
- Remove any residual wax, oil or rust by wiping the frame down with a towel or Scotch-Brite<sup>™</sup> (3M) pad soaked with wax/grease remover.

Bulletin No.: 19-NA-255 January, 2024 Page 7



3611135

8. Using Lloyd's Pure Prep™ Metal Surface Preparation P/N 25418 (10 fluid ounce bottle), or equivalent, saturate a towel or Scotch-Brite™ (3M) pad with the pre-diluted solution and scrub the area well, rendering a foaming of the Pure Prep.™ This will greatly improve adhesion and corrosion resistance in the repair areas.



2708913

**Important:** The frame must be dry and free of wax/oily substances prior to application of the new coating.

- Using a water dampened clean towel, remove any residue and dry the affected area. Dry the repair area completely using an air hose to blow dry the frame.
- Check the repair area for phosphate treatment by wiping it to see if any corrosion residue can be picked up. Correctly treated areas will not have any residue on the surface.



3611138

**Note:** For application of the Lloyds Kryptonite P/N 36500, it can be sprayed, rolled, dipped or painted.

- 11. To retain corrosion protection, apply a light coat of Lloyds Kryptonite™ Metal Treatment\* - P/N 36500 High Temp Satin Black 455 ml (16 oz), or equivalent, to all rusted and bare areas of the frame where the wax coating was removed. This first coat should flash in approximately 3-5 minutes.
- 12. Apply a second coat of Lloyds Kryptonite. This can be a heavy coat; double and triple passes with this product, over a light first coat, are not a problem.

**Note:** Dried Lloyds Kryptonite will perform beautifully over time and actually get harder and more durable as it experiences heat.



36111/13

13. We suggest top coating the Lloyds Kryptonite with Daubert Nox-Rust® P/N X-121B "One Coat Rust Preventative Coating" (aerosol), or equivalent.

**Note:** As shown in the graphic below, besides adding a corrosion resistant layer, it dries to firm, wax-like film which will more closely resemble the appearance of the unrepaired areas of the frame.



3611143

14. Lower the vehicle and allow the final coat to dry as recommended by the manufacturer.

### **Parts Information**

Dealers should obtain 25418 and 36500 by contacting Lloyds by e-mail at sales@lloydslaboratories.com, or by calling 1-800-361-6766.

U.S. Dealers can obtain the X-121B topcoat by contacting the Daubert website at www.daubertchemical.com or inside the U.S. only, by calling 1-800-914-0034.

Canadian dealers must contact the Daubert distributor in Canada, Corrosion Control Coatings Ltd, by faxing the form below to 1-800-563-8078.

Important: ONLY Canadian Dealers should use this form.

Bulletin No.: 19-NA-255 January, 2024 Page 9



February 1, 2022

# GENERAL MOTORS DEALERSHIP ORDER FORM FOR CANADIAN DEALERS ONLY

10.5. Design various de 10.00 filospose by recisetar for Dilator vetote at very filatoric accilentation or habite to 10.5. In president 10.00 filospose by recisetary for Dilator vetote at very filatoric accilentation or habite to 10.5.

			Fee Circlem to: 1-800-563-9070		
Address Bill To	Ć	Ship To:	Doslor#:		
Phone:	Fus.	Contact Name	Fux:		
Root Pres	K12HB Aerosol entive Costing cans per cass) of cases of cases	200	Cost per Case 25.00 - strpping 8 applicable tax Cost per Can. \$18.75 - strpping 8 applicable tax		
800-50 Fax: 800-50	of Coatings Ltd. rot	Paymont Information:  All orders require payment by Credit Card. Please include credit card information  Credit Card #			
Commission:	Ship Duce: Rec'd By:				

# **Warranty Information**

For vehicles repaired under the Bumper-to-Bumper coverage (Canada Base Warranty coverage), use the following labor operation, **and include material cost.** Reference the Applicable Warranties section of Investigate Vehicle History (IVH) for coverage information.

Labor Operation	Description	Labor Time		
1480098*	Remove Frame Wax, Apply Metal Coating	Up to 7.0 hrs		
*This is a unique Labor Operation for Bulletin use only.				

Version	6			
Modified Released November 18, 2019				
	Revised July 22, 2020 – Added 2019 and 2020 T1 Pickup Models.			
	Revised March 10, 2021 – Added 2021 Model Year.			
	Revised February 07, 2022 – Added 2022 Model Year			
	Revised November 07, 2022 – Added 2023 Model Year and Because Lloyds Kryptonite Metal Treatment P/N 36502 Lifelong Rust Protection is No Longer Available we Updated the Product to Lloyds Kryptonite™ Metal Treatment* - P/N 36500 High Temp Satin Black 455 ml (16 oz).			
	Revised January 18, 2024 – Updated Model Years.			